

# **Optima EX**<sup>™</sup>

## Unbleached sack kraft paper extensible

Issued: 04.2024 Cancels: 09.2023

## Technical specification, typical & minimum values

#### Standards

<b>Grammage</b> , g/m <sup>2</sup>			70	80	90	ISO 536
Tolerance, g/m <sup>2</sup>		± 2.5	± 2.5	± 3.0		
Tensile strength index, Nm/g	MD	typ	72	72	72	ISO 1924-3
	UND	min	65	65	65	
	CD	typ	53	53	53	
		min	45	45	45	
Tensile strength, kN/m	MD	typ	5.0	5.8	6.5	ISO 1924-3
	MD	min	4.4	5.0	5.7	
	CD.	typ	3.7	4.2	4.8	
	CD	min	3.0	3.5	3.9	
Strain at break, %	MD	typ	7.4	7.4	7.4	ISO 1924-3
	MD	min	6.5	6.5	6.5	
	CD	typ	7.4	7.4	7.4	
		min	6.5	6.5	6.5	
Tensile Energy Absorption (TEA) index, J/g	MD	typ	3.1	3.1	3.1	ISO 1924-3
	UND	min	2.6	2.6	2.6	
	CD	typ	2.9	2.8	2.8	
		min	2.4	2.3	2.3	
Tensile Energy Absorption (TEA), J/m <sup>2</sup>	MD	typ	224	248	279	ISO 1924-3
	UND	min	182	208	234	
	CD	typ	203	224	252	
	CD	min	168	184	207	
Air permeability Gurley, s max		18			ISO 5636-05	
<b>Cobb 60,</b> g/m² max			32			ISO 535
Moisture, % 7.5±1.5						ISO 287

Laboratory test climate 23°C/50% RH (According to ISO 187). Minimum values are guaranteed.

MD=machine direction, CD=cross direction.

Reel diameters: 120-125 cm. Tolerance of reel width is +/- 2 mm. Reel core size 7.6 cm +/- 1 mm.

Other diameters and cores are possible in cases of full trim of the machine deckle.

Producing mill: Ostroleka, Poland

Stora Enso is committed to continuous quality improvement. Our products' specifications are reviewed, and if necessary, updated with the objective to reflect quality improvements. Please check the latest version from Stora Enso web site.



### Certificates

Quality Management ISO 9001 Environmental Management ISO 14001 Occupational Health and Safety ISO 45001 Product Safety ISO 22000 INS-COC-100054 INS-PEFC-COC-208949

## Ideal storage conditions: 23°C/50% RH

Paper should be stored in a dry, covered and ventilated warehouse. It is recommended that prior to use in production, paper should be stored some time in conditions similar to the conditions in the production hall. The required storage period depends mainly on the volume of paper reel, as well as the temperature difference between the warehouse and production hall.