



February 2008

MagniPress

High brightness and luminosity and excellent opacity available in SC and LWC substances. Outstanding runnability for high performance. Yield advantage through opacity benefits.

End uses
magazines
catalogues
brochures
inserts and flyers

Product description
SC-A+ high white
super calendered uncoated
mechanical paper

Finish
gloss

Printing method
heatset web offset
rotogravure

Producer
Kvarnsveden Mill

Technical specifications

Grammage ISO 536	g/m ²	42	45	48	51	54	56	60
D65-Brightness (D 65/10°)	%	72	72	72	72	72	72	72
Opacity ISO 2471	%	88	88	89	91	92	92	93
Gloss Hunter ISO 8254-4	%	47	48	50	50	50	50	50
Smoothness PPS 1MPa, ISO 8791-4	µm	1.0-1.2	1.0-1.2	1.0-1.2	1.0-1.2	1.0-1.2	1.0-1.2	1.0-1.2
Bulk, ISO 534	cm ³ /g	0.9	0.9	0.83	0.83	0.83	0.83	0.83
Thickness ISO 534	µm	39	41	43	45	46	48	50

Reel specifications

trimmed width	1040/543 cm
core	76/150 mm
max. width	450 cm
min. width	40 cm
max. diameter	150 cm
min. diameter	100 cm
max. weight	10000 kg

Wrapping

test and kraft liner
polyethylene

Environment

recyclable paper
recyclable packaging materials