



March 2008

NeoPress

With high printed gloss and very good printability NeoPress offers an extraordinary good cost/quality ratio. Excellent opacity.

End uses
magazines with high ink coverage
demanding catalogues
advertising brochures
leaflets
flyers

Product description
LWC mechanical coated paper

Finish
gloss

Printing method
heatset web offset

Producer
Arapoti Mill

Technical specifications

| | | 54 | 57 | 60 | 65 | 70 | 80 |
|--|--------------------|------|------|------|------|------|------|
| Grammage ISO 536 | g/m ² | 54 | 57 | 60 | 65 | 70 | 80 |
| D65-Brightness (D 65/10°) | % | 82 | 82 | 82 | 82 | 82 | 82 |
| CIE Whiteness ISO 11476, C/2° | % | 88 | 88 | 88 | 88 | 88 | 88 |
| Y-value CIE, D 65/10° | % | 77 | 77 | 77 | 77 | 77 | 77 |
| Opacity ISO 2471 | % | 89 | 90 | 91 | 93 | 95 | 95 |
| Gloss Hunter , ISO 8254-1 | % | 50 | 50 | 50 | 50 | 50 | 50 |
| Smoothness PPS 1MPa , ISO 8791-4 | µm | 1.1 | 1.1 | 1.1 | 1.1 | 1.1 | 1.1 |
| Bulk ISO 534 | cm ³ /g | 0.87 | 0.85 | 0.85 | 0.85 | 0.85 | 0.85 |
| Thickness ISO 534 | µm | 47 | 49 | 51 | 55 | 60 | 68 |

Reel specifications

| | |
|---------------|---------|
| trimmed width | 524 cm |
| core | 76 mm |
| max. width | 191 cm |
| min. width | 40 cm |
| max. diameter | 120 cm |
| min. diameter | 100 cm |
| max. weight | 3000 kg |

Wrapping

test and kraft liner
polyethylene

Environment

oxygen bleached pulp quality
recyclable paper
recyclable packaging materials