

January 2012

TerraPress

High-bright coated mechanical paper for highest demands in printability and runnability. High printed gloss. Competitive opacity yield. Fine screening up to 80 lines/cm or 200/inch.

HSWO

End uses

high-quality magazines
demanding advertising material
leaflets
flyers

Product description

LWC/MWC slightly mechanical coated paper

Finish

gloss

Printing method

heatset web offset

Producer

Corbehem Mill (57-70 g/m²)
Kabel Mill (75-90 g/m²)

Technical specifications

	g/m ²	57	60	65	70	75	80	90
Grammage ISO 536								
D65-Brightness D 65/10°	%	87	87	87	87	90	90	90
CIE Whiteness ISO 11476, C/2°	%	93	93	93	93	95	95	95
Opacity ISO 2471	%	90.0	91.0	92.0	93.0	93.0	93.5	95.0
Gloss Hunter, ISO 8254-1	%	57	60	60	62	63	63	63
Smoothness PPS 1MPa, ISO 8791-4	µm	1.0	1.0	1.0	1.0	1.0	1.0	1.0
Bulk ISO 534	cm ³ /g	0.85	0.85	0.85	0.85	0.80	0.80	0.80
Thickness ISO 534	µm	49	51	55	60	62	64	70

Reel specifications

trimmed width
core
max. width
min. width
max. diameter
min. diameter
max. weight

Corbehem

860 cm
76/150 mm
300 cm
44 cm
125 cm
100 cm
5000 kg

Kabel

718 cm
76/150 mm
320 cm
38.8 cm
130 cm
100 cm
7000 kg

Wrapping

polyethylene laminated
kraft paper

Environment

renewable fibre
recyclable paper
recyclable packaging materials



storaenso



PRESSSELECTION