

January 2012

TurnoPress

HSWO

With high printed silk and very good printability, TurnoPress offers an extraordinary good cost/quality ratio. Excellent opacity.

End uses

High print run magazines and demanding catalogues
advertising brochures
leaflets and flyers

Product description

LWC mechanical coated paper

Finish

silk

Printing method

heatset web offset

Producer

Arapoti Mill

Technical specifications

Grammage ISO 536	g/m ²	56
D65-Brightness D 65/10°	%	66
CIE Whiteness ISO 11476, C/2°	%	57
Opacity ISO 2471	%	96.0
Gloss Hunter, ISO 8254-1	%	43
Smoothness PPS 1MPa, ISO 8791-4	µm	1.3
Bulk ISO 534	cm ³ /g	0.93
Thickness ISO 534	µm	52

Reel specifications

trimmed width	524 cm
core	76 mm
max. width	196 cm
min. width	40 cm
max. diameter	120 cm
min. diameter	100 cm
max. weight	3000 kg

Wrapping

test and kraft liner polyethylene

Environment

oxygene bleached pulp quality
renewable fibre
recyclable paper
recyclable packaging materials