

# EnviPress

## 悦印超级压光纸

by Stora Enso

源自斯道拉恩索



EnviPress is a SC-B soft calendered uncoated mechanical paper. It is made out of 100% recycled fibre.

悦印超级压光纸使用100%回收纤维。

- High print gloss 高的印刷光泽度
- Suitable for rotogravure and offset printing 适合凹印和胶印印刷
- Shade similar to standard SC qualities 标准超级压光纸品质

<b>HMD 75@9B81 G9G</b>	<b>用途</b>	<b>7C@CI F DFC: 49 色彩管理文件</b>
Inserts	宣传广告	FOGRA 54
Flyers	插页	
Brochures	手册	<b>DF-BHB; A 9H-C8G 印刷方式</b>
Mass circulation TV magazines	杂志	HSWO 商业轮转
Supplements	增刊	Rotogravure 凹印

target values 目标值	L*	a*	b*	Fluorescence (ISO 12647-2)
Langerbrugge ISO 5631-3 (D50/2°)	87	-0.4	5.0	Faint

### TECHNICAL SPECIFICATIONS (target values) 技术指标 (目

Substance:	克重	g/m <sup>2</sup>	42.5	45	49	52	56
Brightness	白度	ISO 2470-2 (D65/10°) %	66	67	67	67	67
CIE Whiteness	CIE白度	ISO 11476 (C/2°) %	43	43-47	43-47	43-47	43-47
Opacity	不透明度	ISO 2471 (D65/10°) %	88	89	91	92-93	93-94
Gloss Hunter	光泽度	ISO 8254-1 %	36	37	38	38-40	38-40
Thickness	厚度	ISO 534 μm	41	43	45	47	50
Bulk	松厚度	ISO 534 cm <sup>3</sup> /g	0.96	0.94	0.92	0.90	0.89
Smoothness	平滑度	ISO 8791-4 PPS (1MPa) μm	1.5	1.5	1.5	1.5	1.5

**F 99@GD97 ÷ 75H-CBG 纸卷规格**  
**@5B; 9F 6FI ; ; 9**

Cores: 76 mm, 150 mm  
卷芯: 76毫米, 150毫米  
Trimmed width: 5720 mm  
整副宽度: 5720毫米  
Width: min. 360 mm, max. 4500 mm  
纸卷宽度: 最小宽度360毫米, 最大宽度 4500毫米  
Diameters: min. 1000 mm, max. 1500 mm  
纸卷直径: 最小直径1000毫米, 最大直径1500毫米  
Weight: max. 7700 kg  
重量: 最大纸卷重量7700千克

**CERTIFICATES 证书**  
**Langerbrugge Mill Langerbrugge工厂**  
The EU Ecolabel FI/011/007  
欧洲环境标志 EU Ecolabel FI/011/007  
The Blue Angel UZ 14 27955  
EMAS  
ISO 9001  
ISO 14001  
ISO 50001  
OHSAS 18001  
FSC® CoC, license code FSC® C015932  
PEFC™ CoC, licence code PEFC/02-31-86

**ENVIRONMENT 环保**  
Renewable fibre  
可回收纤维  
Recyclable paper  
可回收纸张  
Recyclable packaging materials  
可回收包装材料

### Storage and Handling 储存和使用

- Store the paper in a humidity and temperature controlled area at 50% relative humidity and room temperature between 19°C and 23°C.
- 在温度19°C -23°C和相对湿度50%的环境中, 储存纸张。
- If the paper is stored in non-air conditioned warehouse, it is absolutely necessary to allow a stabilisation period in the print room.
- 如果纸张在使用前, 储存于没有温湿度控制的仓库, 则最好在印刷使用前提使之适应印刷环境
- Open the protective wrapping at the moment of use.
- 仅在使用时打开包装。

Producer: Langebrugge Mill Langerbrugge工厂

Updated: 03 December 2019 更新时间: 2019-12-3