

# NovaPress Silk

## 诺华雅光印刷纸

by Stora Enso 源自斯道拉恩索



NovaPress Silk is a special coated mechanical silk matt printing paper.

诺华雅光印刷纸是高品质丝光涂布纸。

- High print quality makes it ideal for elegant magazines 越的印刷品质满足高端杂志的要求
- Excellent brightness and opacity ratio 杰出的白度和不透明度的结合
- Ideal for demanding advertising in big editions 适合高品质广告要求

**TYPICAL END USES** 用途  
Brochures 手册  
Catalogues 样本  
Magazines 杂志期刊  
Periodicals 期刊  
Supplements 增刊

**PRINTING METHODS** 印刷方式  
HSWO 商业轮转印刷

**COLOUR PROFILE** 色彩管理文件  
FOGRA 39

**FINISH** 纸张特性  
Silk 丝光光泽

target values 目标值	L*	a*	b*	Fluorescence (ISO 15397)
ISO 5631-3 (D50/2°)	93.0	0.9	-3.5	Low

### TECHNICAL SPECIFICATIONS (target values) 技术指标 (目标值)

Substance	克重		g/m <sup>2</sup>	60	65	70	75	80	90	100	115
Brightness	白度	ISO 2470-2 (D65/10°)	%	92	94	95	95	97	98	100	101
CIE Whiteness	CIE 白度	ISO 11476 (C/2°)	%	94.0	96.0	98.0	100.0	101.0	102.0	103.5	104.5
Opacity	不透明度	ISO 2471 (D65/10°)	%	94.0	95.0	96.0	96.5	97.0	98.0	98.5	99.0
Gloss Hunter	光泽度	ISO 8254-1	%	36	36	36	36	38	39	40	40
Thickness	光泽度	ISO 534	µm	60	65	70	75	80	90	100	120
Bulk	松厚度	ISO 534	cm <sup>3</sup> /g	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00
Smoothness	平滑度	ISO 8791-4 PPS (1MPa)	µm	1.3	1.3	1.3	1.25	1.25	1.25	1.30	1.30

### REEL SPECIFICATIONS 纸卷规格

Core: 76 mm/150 mm

卷芯: 76毫米

Width: min. 350 mm/max. 2900 mm

纸卷宽度: 最小宽度350毫米, 最大宽度2900毫米

Diameters: 900 - 1500 mm

纸卷直径: 最小直径900毫米, 最大直径1500毫米

Max weight: 3500 kg

重量: 最大纸卷重量3500千克

### CERTIFICATES 证书

EU Ecolabel FI/011/007

欧洲环境标志 EU Ecolabel FI/011/007

ISO 9001

ISO 14001

ISO 50001

OHSAS 18001

FSC® CoC, license code FSC® C015932

PEFC™ CoC, licence code PEFC/02-31-86

Inspected Paper (\*)

### ENVIRONMENT 环保

Renewable fibre

可回收纤维

Recyclable paper

可回收纸张

Recyclable packaging materials

可回收包装材料

### STORAGE AND HANDLING 储存和使用

- Store the paper in a humidity and temperature controlled area at 50% relative humidity and room temperature between 19°C and 23°C.  
· 在温度19°C -23°C和相对湿度50%的环境中, 储存纸张。
- If the paper is stored in non-air conditioned warehouse, it is absolutely necessary to allow a stabilisation period in the print room.  
· 如果纸张在使用前, 储存于没有温湿度控制的仓库, 则最好在印刷使用前提使之适应印刷环境。
- Open the protective wrapping at the moment of use.  
· 仅在使用时打开包装。