

Exo 68

by Stora Enso



Exo is a machine finished uncoated mechanical newsprint speciality.

- First class printability and runnability
- Overall cost efficiency

PRODUCER

Anjala Mill

TYPICAL END USES

Inserts
Supplements
Advertisements
Magazines
Special Newspapers
Free sheets

PRINTING METHODS

CSWO
HSWO
InkJet

ICC-PROFILE

Download: [Technical Resource Centre](#)

CHARACTERIZATION DATA

FOGRA 42

L* a* b* target values	L*	a*	b*	Fluorescence (ISO 12647-2)
Exo 68 ISO 5631-3 (D50/2°)	87.1	0.7	2.4	Faint

TECHNICAL SPECIFICATIONS (target values)

Substance		g/m ²	49	52	55	60
Brightness	ISO 2470-2 (D65/10°)	%	68	68	68	68
Whiteness	CIE, ISO 11476 (C/2°)	%	56	56	56	56
Opacity	ISO 2471	%	92	93	95	96
Thickness (indicative)	ISO 534	µm	78	83	88	96
Bulk (indicative)	ISO 534	cm ³ /g	1.6	1.6	1.6	1.6
Smoothness	PPS 1 MPa, ISO 8791-4	µm	3.6	3.6	3.6	3.6

REEL SPECIFICATIONS

Core: 76 mm
Trimmed width: 8550 mm
Width: min. 300 mm, max. 2500 mm
Diameters: 1000, 1060, 1150, 1250 mm
Max. weight: 3000 kg

CERTIFICATES

EU Ecolabel FI/011/007
Quality ISO 9001
Environment ISO 14001
Health & Safety ISO 45001
Energy ISO 50001
[FSC® CoC \(FSC® C015932\)](#) *
[PEFC™ CoC \(PEFC/02-31-86\)](#) *
(* FSC or PEFC paper is only delivered on customer request.)
For more information:
www.storaenso.com/paper-sustainability

ENVIRONMENT

Renewable fibre
Recyclable paper
Recyclable packaging materials

STORAGE AND HANDLING

- Store the paper in a humidity and temperature controlled area at 50% relative humidity and room temperature between 19°C and 23°C.
- If the paper is stored in non-air conditioned warehouse, it is absolutely necessary to allow a stabilisation period in the print room.
- Open the protective wrapping at the moment of use.