# **Exo** 72

by Stora Enso



Exo is a machine finished uncoated mechanical newsprint speciality.

- First class printability and runnability
- Overall cost efficiency

PRODUCER Anjala Mill

<b>TYP</b>	ICA	I F	ND	USES

Inserts
Supplements
Advertisements
Magazines
Special Newspapers
Free sheets

#### **PRINTING METHODS**

CSWO HSWO InkJet

## CHARACTERIZATION DATA

FOGRA 42

L* a* b* target values	L*	a*	b*	Fluorescence (ISO 12647-2)
Exo 72 ISO 5631-2 (D65/10°)	88.6	-1.2	3.0	Faint

#### **TECHNICAL SPECIFICATIONS (target values)**

Substance		g/m²	52	55
Brightness	ISO 2470-2 (D65/10°)	%	72	72
Whiteness	CIE, ISO 11476 (C/2°)	%	60	60
Opacity	ISO 2471	%	93	93
Thickness (indicative)	Таррі Т411	μm	83	88
Bulk (indicative)	ISO 534	cm³/g	1.6	1.6
Smoothness	PPS 1 MPa, ISO 8791-4	μm	3.6	3.6

#### **REEL SPECIFICATIONS**

Core: 76 mm Trimmed width: 5400 mm Width: min. 300 mm, max. 2500 mm Diameters: 1000, 1150, 1250 mm

Max. weight: 3000 kg

### CERTIFICATES

EU Ecolabel FI/011/002 Quality ISO 9001 Environment ISO 14001 Health & Safety ISO 45001 Energy ISO 50001 FSC®-CoC (FSC®-C127282) \*

PEFC -CoC (PEFC/02-31-247) \*

\* FSC and PEFC certified paper available upon request

For more information:

www.storaenso.com/download-centre

#### **ENVIRONMENT**

Renewable fibre
Recyclable paper
Recyclable packaging materials

#### STORAGE AND HANDLING

- Store the paper in a humidity and temperature controlled area at 50% relative humidity and room temperature between 19°C and 23°C.
- If the paper is stored in non-air conditioned warehouse, it is absolutely necessary to allow a stabilisation period in the print room.
- Open the protective wrapping at the moment of use.