

LumiLeaf

by Stora Enso



Slightly mechanical uncoated paper for multicolor offset printing.

- Excellent opacity in low basis weights
- Good runnability
- Easy-folding

PRODUCER

Veitsiluoto Mill

TYPICAL END USES

Medical and cosmetic leaflets
Manuals and booklets
Books

PRINTING METHODS

Offset
Laser

Substance		g/m ²	35	40	45	50	55	60
Brightness	D65	%	84	85	85	85	85	85
Whiteness	CIE	%	105	105	105	105	105	105
Opacity	ISO	%	82	85	87	89	90	91
Bulk		cm ³ /g	1.22	1.32	1.32	1.32	1.32	1.32
Thickness		µm	43	53	60	66	73	80
Roughness	Bendtsen	ml/min	40	80	90	120	130	140
Moisture		%	5	5	5	5	5	5

CERTIFICATES Veitsiluoto

ISO 9001
ISO 14001
OHSAS 18001
EU Ecolabel
Nordic Ecolabel
PEFC™ CoC
FSC® CoC

STORAGE AND HANDLING

- Store the paper in a humidity and temperature controlled area at 50% relative humidity and room temperature between 19° and 23° C.
- If the paper is stored in non-air conditioned warehouse, it is absolutely necessary to allow a stabilisation period in the print room.
- Open the protective wrapping at the moment of use.