

StellaPress H

by Stora Enso



StellaPress H is a machine-finished matt coated mechanical paper for offset printing.

- Good readability due to matt surface
- Good runnability

PRODUCER

Anjala Mill

TYPICAL END USES

Magazines
Leaflets
Supplements
Inserts

PRINTING METHODS

HSWO
SFO

FINISH

Matt

COLOUR PROFILE

STORA ENSO
STELLAPRESS.ICC

To download our icc profiles follow this link:

<https://info.storaenso.com/paper-resourcecentre-prepress>

L* a* b* target values	L*	a*	b*
ISO 5631-3 (D50/2°)	91.7	-0.5	-1.0

TECHNICAL SPECIFICATIONS (target values)

Substance		g/m ²	52	54	57	60	65	70	80
Bulk (indicative)	ISO 534	cm ³ /g	1.15	1.15	1.15	1.15	1.15	1.15	1.15
Thickness (indicative)	ISO 534	µm	60	62	65	70	75	80	92
Brightness	ISO 2470-2 (D65/10°)	%	87	87	87	87	87	87	87
Opacity	ISO 2471	%	90	91	92	93	94	95	95
Gloss Hunter	ISO 8254-1	%	20	20	20	20	20	20	20
Smoothness	ISO 8791-4 PPS (1MPa)	µm	2.5	2.5	2.5	2.5	2.5	2.5	2.5

REEL SPECIFICATIONS

Core: 76 mm
Trimmed width: 52 g/m² 5350 mm, 54 g/m² 5380 mm,
57-80 g/m² 5400 mm
Width: min. 300 mm, max. 2500 mm
Diameters: 1000 mm, 1200 mm, 1250 mm
Max. weight: 3000 kg

CERTIFICATES

The EU Ecolabel FI/011/007
ISO 9001
ISO 14001
ISO 50001
OHSAS 18001
FSC® CoC, license code FSC® C015932 *
PEFC™ CoC, licence code PEFC/02-31-86 *
(* FSC or PEFC paper is only delivered on customer request.)

ENVIRONMENT

Renewable fibre
Recyclable paper
Recyclable packaging materials

STORAGE AND HANDLING

- Store the paper in a humidity and temperature controlled area at 50% relative humidity and room temperature between 19°C and 23°C.
- If the paper is stored in non-air conditioned warehouse, it is absolutely necessary to allow a stabilisation period in the print room.
- Open the protective wrapping at the moment of use.