


Cupforma Special[™] PE

Pigment coated cup board with PE coating

Cupforma Special PE is a board with a three layer fibre construction including CTMP (chemi-thermomechanical pulp) in the middle layer and a fully coated top side. It has a PE coating on the reverse side.



Top layer (bleached sulphate pulp) Middle layer (bleached sulphate pulp + CTMP) Back layer (bleached sulphate pulp) PE coating

> Issued: 06.2020 Cancels: 08.2017

Technical specification

		5+15	210+15	230+15	255+15	270+15	295+15	320+15	350+15	
Property / Unit	Tolerance	195+.	210	230	255	270	295	320	350	Standards
Polymer coated board:										
Grammage, g/m ²	±7%	210	225	245	270	285	310	335	365	ISO 536
PE reverse, g/m ²	±2	15	15	15	15	15	15	15	15	Mill method
Thickness, μm	±9%	270	290	330	360	400	440	480	520	ISO 534
Baseboard:										
Grammage, g/m ²	±6%	195	210	230	255	270	295	320	350	ISO 536
Thickness, µm	±8%	260	280	320	350	390	430	470	510	ISO 534
Bending resistance L&W 15° MD, mN	min -20%	120	155	215	270	360	475	600	760	ISO 2493-1
Bending resistance L&W 15° CD, mN	min -20%	55	70	95	125	170	210	270	340	130 2493-1
Moisture %	min 5.0%	6.5	6.5	6.5	6.5	6.5	6.5	6.5	6.5	ISO 287
Brightness D65/10, Top		85	85	85	85	85	85	85	85	ISO 2470-2
Surface Smoothness, PPS 10, µm, Top	max 1.7	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2	ISO 8791-4
Surface Smoothness, Bendtsen, ml/min	max 130	40	40	40	40	50	50	50	50	ISO 8791-2
Stretch CD, %		6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	ISO 1924-3

All properties according to Imatra Mill measurements from board machine production. Laboratory test climate 23°C/50% RH (according to ISO 187). Tolerances based upon 95% confidence limits, apply to delivered reel/pallet average.





Cupforma Special[™] PE

Pigment coated cup board with PE coating

Certificates

Quality management ISO 9001 Environmental management ISO 14001 Product safety FSSC 22000 Product safety ISO 22000 Occupational health and safety ISO 45001 Energy management ISO 50001



Promoting Sustainable Forest Management Www.pefc.fi

FSC and PEFC certified board available upon request.



Paperboard is recyclable

Key characteristics and main enduses

Cupforma Special PE is a sustainable choice; a high-quality carton board specially designed for cups and for very high requirements on printing. It is food-safe, ecological, and works smoothly and consistently in cup converting. It is also economical as the board's structure provides the required stiffness; resulting in light, yet functional cups. The fully pigment coated top side is very smooth, which ensures high-quality print results in flexographic, offset, and digital printing to showcase brands. Combined with PE coating, Cupforma Special is sealed easily into a cup and used for ice cream cups out-of-home and other packaging cups.

Printing and finishing techniques

The product can be used for different printing techniques such as offset, flexo and digital printing. It is important to check possible limitations of the printing and converting equipment and ensure that the basis weight of the board fits the tooling to be used. Since a wide variety of digital printing equipment is available in the market, it is important that a new commercial digital print job is always preceded by a trial run, including all required printing and converting process phases.

Storage recommendations

For optimal printing results, the moisture proof wrapping should not be removed until the board has reached the temperature of the press room.

Pallet/Reel Weight (kg)	Difference in temperature between board and press room (press room temp. approx. 20°C)							
	10°C	20°C	30°C					
400 kg	2 days	2 days	3 days					
800 kg	2 days	3 days	4 days					
1200 kg	2 days	4 days	5 days					

The product properties, according to the specifications, are guaranteed for 12 months after the production date. In order to ensure product safety, the product must be well wrapped and stored indoors, sheltered from rain and snow. The recommended storage conditions are 50-55% relative humidity and $20-23^{\circ}$ C.

For the Corona treatment, we recommend using the board within 12 months of the production date; after this period, the treatment level should be tested before printing or gluing.

