


Ensocoat[™]

Fully coated multilayer SBS board with light coated reverse

Ensocoat is a luxurious, coated SBS (solid bleached sulphate) board with a three-layer fibre construction of chemical pulp. It is double-pigment-coated on the top side, with one layer of pigment coating on the reverse side.



Double pigment coating Chemical pulp Chemical pulp Chemical pulp Light pigment coating

> Issued: 03.2024 Cancels: 09.2021

Technical specification

Typical properties, US												
Caliper, pt		7.9	9.1	10.4	10.6	11.8	13.0	14.4	16.3	17.5	19.1	
Nominal basis weight, lbs/1000 sq.Ft.		38.9	43.0	45.1	47.1	51.2	56.3	61.4	67.6	71.7	77.8	
Bending moment Taber MD, gcm		37	52	61	79	103	133	185	247	286	364	
Bending moment Taber CD, gcm		17	24	31	37	49	64	89	118	133	172	
Scott Bond, Lbfft/1000 in ²		105	105	105	105	105	105	105	105	105	105	
Typical properties, Metric	Tolerance											Method
Thickness, μm	±4%	200	230	265	270	300	330	365	415	445	485	ISO 534
Nominal basis weight, g/m²	±4%	190	210	220*	230	250	275	300	330	350	380	ISO 536
Bending resistance L&W 15° MD, mN	-15%	75	105	120	160	210	270	375	500	580	740	ISO 2493-1
Bending resistance L&W 15° CD, mN	-15%	35	50	60	75	100	130	180	240	270	350	150 2493-1
Bending moment Taber 15° MD, mNm	-15%	3.6	5.1	6.0	7.7	10.1	13.0	18.1	24.2	28.0	35.7	
Bending moment Taber 15° CD, mNm	-15%	1.7	2.4	3.0	3.6	4.8	6.3	8.7	11.6	13.0	16.9	
Bending stiffness DIN 5° MD	-15%	6.4	8.9	11.5	13.6	17.9	23.0	31.9	42.5	49.3	62.9	
Bending stiffness DIN 5° CD	-15%	3.0	4.3	5.0	6.4	8.5	11.1	15.3	20.4	23.0	29.8	
Moisture, %	±1, ±1.5 **	6.5	6.5	6.5	6.5	6.5	6.5	6.5	6.0	6.0	6.0	ISO 287
ISO Brightness C/2°, %, Top	min. 92	95	95	95	95	95	95	95	95	95	95	ISO 2470-1
ISO Brightness C/2°, %, Reverse	min. 90	93	93	93	93	93	93	93	93	93	93	150 2470-1
Brightness D65/10°, %, Top		103	103	103	103	103	103	103	103	103	103	ISO 2470-2
CIE Whiteness D65/10°, Top		135	135	135	135	135	135	135	135	135	135	100 44 475
CIE Whiteness D65/10°, Reverse		130	130	130	130	130	130	130	130	130	130	ISO 11475
L* D65/10°, Top		96.5	96.5	96.5	96.5	96.5	96.5	96.5	96.5	96.5	96.5	
a* D65/10°, Top		2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	ISO 5631-2
b* D65/10°, Top		-10.5	-10.5	-10.5	-10.5	-10.5	-10.5	-10.5	-10.5	-10.5	-10.5	
Surface Smoothness PPS 10, µm, Top	max 1.4	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	100 0704 4
Surface Smoothness PPS 10, µm, Reverse		<4.0	<4.0	<4.0	<4.0	<4.0	<4.0	<5.0	<5.0	<5.0	<5.0	ISO 8791-4
Surface Smoothness Bendtsen, ml/min, Top		20	20	20	20	20	20	20	20	20	20	100 8701 0
Surface Smoothness Bendtsen, ml/min, Reverse		<100	<100	<200	<200	<200	<200	<200	<300	<300	<400	ISO 8791-2
Gloss 75°, %, Top		48	48	48	48	48	48	48	48	48	48	ISO 8254-1
Scott Bond, J/m ²	min 140	220	220	220	220	220	220	220	220	220	220	TAPPI 569 om-09
Robinson chocolate test		-10.5 <th< td=""><td>EN 1230-2</td></th<>				EN 1230-2						

All properties according to Imatra Mill measurements from board machine production. Laboratory test climate 23°C/50% RH (According to ISO 187). Tolerances based upon 95% confidence limits, apply to delivered reel/pallet average.

Bending moment Taber 15° and Bending resistance L&W 15° are binding, Bending stiffness DIN 5° are indicative. Bending moment Taber 15° calculated from Bending resistance L&W 15°.





Ensocoat[™]

Fully coated multilayer SBS board with light coated reverse

Certificates

Quality management ISO 9001 Environmental management ISO 14001 Product safety FSSC 22000 Occupational health and safety ISO 45001 Energy management ISO 50001





FSC and PEFC certified board available upon request.



Paperboard can be recycled

Key characteristics and main enduses

Ensocoat is Stora Enso's flagship board, crafted to meet the demands of the graphical industry and luxury packaging. Its surface smoothness, printing performance, brightness, whiteness, UV-light resistance and reverse-side print result have been optimized to impress even in the most demanding applications. Produced from responsibly sourced, certified raw materials, it serves as the industry standard for high performance and sustainability. Ensocoat is ideal for cosmetic, perfume, premium chocolate, pharmaceutical and healthcare packaging. It is also used for greeting cards, book covers, folders, calendars, stationery products and displays. Thanks to the three-layer fibre construction, Ensocoat has outstanding strength, folding, embossing and converting properties. This product is compostable in industrial and home composting and can be collected together with food waste in most collecting schemes.

Printing and finishing techniques

The product can be used with different printing techniques such as offset, flexo and digital printing. In digital printing, the product is suitable for several different sheet- or web-fed presses. Dry or liquid toner technology can be used, although in some cases, pretreatment of the substrate might be required. The latest certification status can be verified on the press manufacturer's website or with local Stora Enso representatives. It is important to check the limitations of the equipment, particularly because of the exceptional difference in the thickness and stiffness of board compared with paper in the same grammages. When running thicker substrates, the press manufacturer's recommendations should be referred to for optimal grain direction. Essentially all of the same finishing processes apply to both digitally printed and offset printed work. Since a wide variety of digital printing equipment is available in the market, it is important that a new commercial print job is always preceded by a trial run, including all required printing and converting process phases. The product works very well with different finishing techniques, such as embossing, hot foil stamping and others. It is suitable for laser coding. Certificate according to PTS-DF 105/2019 is available upon request.

Storage recommendations

For optimal printing results, the moisture proof wrapping should not be removed until the board has reached the temperature of the press room.

Pallet/Reel Weight (kg)	Difference in temperature between board and press room							
	50°F	68°F	86°F					
881 lbs	2 days	2 days	3 days					
1763 lbs	2 days	3 days	4 days					
2645 lbs	2 days	4 days	5 days					

The product properties, according to the specifications, are guaranteed for 12 months after the production date.

In order to ensure product safety, the product must be well wrapped and stored in its original cover indoors,

sheltered from rain and snow. The recommended storage conditions are 50–55% relative humidity and 68–73.4°F.

