


# Performa Cream™ PE

### Fully coated CTMP board with cream reverse

Performa Cream PE is a polyethylene-coated GC2 board with a three-layer fibre construction and CTMP (chemithermomechanical pulp) in the middle layer. It is triple-pigment-coated on the top side, and the reverse cream side is coated with transparent LDPE. Performa Cream PE is also available hard-sized (HS).



Issued: 03.2024 Cancels: 12.2017

### **Technical specification**

Property / Unit	Tolerance	180×12	200×12	220×12	230×12	245×12	260×12	290×12	315×12	340×12	360×15	Standard
Polymer coated board:												
Grammage, g/m²		192	212	232	242	257	272	302	327	352	372	ISO 536
LDPE reverse, g/m²		12	12	12	12	12	12	12	12	12	12	Mill method
Thickness, µm		297	322	352	372	417	452	512	572	622	662	ISO 534
Baseboard:												
Grammage, g/m²	±4%	180	200	220	230	245	260	290	315	340	360	ISO 536
Thickness, µm	±5%	285	310	340	360	405	440	500	560	610	650	ISO 534
Bending resistance L&W 15° MD, mN	-15%	115	172	224	266	320	385	510	670	825	930	
Bending resistance L&W 15° CD, mN	-15%	50	72	94	111	140	170	230	300	375	420	ISO 2493
Bending moment Taber 15° MD, mNm	-15%	5.6	8.3	10.8	12.8	15.5	18.6	24.6	32.4	39.8	44.9	
Bending moment Taber 15° CD, mNm	-15%	2.4	3.5	4.5	5.4	6.8	8.2	11.1	14.5	18.1	20.3	
Bending stiffness DIN 5° MD, mNm	-15%	11.0	15.3	19.6	22.6	29.9	36.4	51.2	64.0	78.7	91.8	
Bending stiffness DIN 5° CD, mNm	-15%	5.0	5.8	7.5	8.8	12.1	15.3	21.9	27.5	32.1	40.5	
Moisture, %	±1, ±1.5 *	7.7	7.7	7.8	7.9	7.9	8.0	8.4	8.7	8.9	9.1	ISO 287
ISO Brightness C/2°, %, Top	min. 87	90	90	90	90	90	90	90	90	90	90	ISO 2470-1
Brightness D65/10°, %, Top		97	97	97	97	97	97	97	97	97	97	ISO 2470-2
CIE Whiteness D65/10°, Top		120	120	120	120	120	120	120	120	120	120	ISO 11475
Surface Smoothness, PPS 10, µm, Top	max. 1.7	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	ISO 8791-4
Gloss 75°, %		45	45	45	45	45	45	45	45	45	45	ISO 8254-1
Scott Bond, J/m²	min. 100	145	145	145	145	145	145	145	145	145	145	TAPPI 569
Edge wicking**, kg/m²	max. 1.0	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	
Cobb 60, g/m², Top	max. 60	30	30	30	30	30	30	30	30	30	30	ISO 535
Robinson chocolate test				max	0.5 for o	ne year	storage	in reels,	/pallet			EN1230-2

\*) For 315 – 360 g/m<sup>2</sup>

\*\*) For hardsized





## Performa Cream™ PE

## Fully coated CTMP board with cream reverse

#### **Certificates**

Quality management ISO 9001 Environmental management ISO 14001 Product safety FSSC 22000 Occupational health and safety ISO 45001 Energy management ISO 50001





FSC and PEFC certified board available upon request.



Paperboard can be recycled

### Key characteristics and main enduses

Performa Cream PE provides excellent value, runnability and performance in applications that require protection against humidity. Performa Cream PE is typically used for chocolate and confectionery, and frozen and chilled food products. Thanks to the triple-pigment-coated top side, combined with high brightness and whiteness for optimal visual appearance, Performa Cream gives a very good print result.

### Printing and finishing techniques

The product can be used with different printing techniques such as offset, flexo and rotogravure. The product works very well with different finishing techniques, such as embossing, hot foil stamping and others. It is suitable for laser coding and ink jet marking. Certificates according to PTS-DF 105/2019 and PTS-DF 103/2022 are available upon request.

### Storage recommendations

For optimal printing results, the moisture proof wrapping should not be removed until the board has reached the temperature of the press room.

Pallet/Reel Weight (kg)	Difference in temperature between board and press room (press room temp. approx. 20°C)						
	10°C	20°C	30°C				
400 kg	2 days	2 days	3 days				
800 kg	2 days	3 days	4 days				
1200 kg	2 days	4 days	5 days				

The product properties, according to the specifications, are guaranteed for 12 months after the production date. In order to ensure product safety, the product must be well wrapped and stored in its original cover indoors, sheltered from rain and snow. The recommended storage conditions are 50–55% relative humidity and 20–23°C.

For the Corona treatment, we recommend using the board within 12 months of the production date; after this period, the treatment level should be tested before printing or gluing.

