


Trayforma[™] PP

Bleached tray board for microwave oven

Trayforma PP is a bleached virgin-fibre board with a three layer fibre construction with CTMP (chemithermomechanical pulp) in the middle layer and a polypropylene coating on the reverse side.



Technical specification

| Property/Unit | Tolerance | 190+20 | 230+20 | 310+20 | 350+20 | 390+20 | 420+20 | Standard |
|---|------------|--------|--------|--------|--------|--------|--------|-------------|
| PP coated board: | | | | | | | | |
| Grammage, g/m² | ± 6 % | 210 | 250 | 330 | 370 | 410 | 440 | ISO 536 |
| PP reverse, g/m² | ± 2 | 20 | 20 | 20 | 20 | 20 | 20 | Mill method |
| Thickness, µm | ± 6 % | 275 | 325 | 440 | 485 | 565 | 630 | ISO 534 |
| Baseboard: | | | | | | | | |
| Grammage, g/m² | ± 6 % | 190 | 230 | 310 | 350 | 390 | 420 | ISO 536 |
| Thickness, µm | ± 6 % | 255 | 305 | 420 | 465 | 545 | 610 | ISO 534 |
| Bending resistance L&W 15° MD, mN | min -25% | 100 | 160 | 420 | 550 | 800 | 1000 | 100 0400 4 |
| Bending resistance L&W 15° CD, mN | min -25% | 40 | 60 | 160 | 200 | 300 | 400 | ISO 2493-1 |
| Bending moment Taber 15° MD, mNm | min -25% | 4.8 | 7.7 | 20.2 | 26.4 | 38.4 | 48.3 | |
| Bending moment Taber 15° CD, mNm | min -25% | 1.9 | 2.9 | 7.7 | 9.6 | 14.4 | 19.3 | |
| Moisture, % | min 7.5% | 9.5 | 9.5 | 9.5 | 9.5 | 9.5 | 9.5 | ISO 287 |
| Brightness D65/10, %, top | | 83 | 83 | 83 | 83 | 83 | 83 | ISO 2470-2 |
| Surface Smoothness, Bendtsen, ml/min, top | max + 28 % | 250 | 250 | 300 | 320 | 450 | 600 | 100 0704 0 |
| Surface Smoothness, Bendtsen, ml/min, reverse | max + 28 % | 400 | 500 | 700 | 800 | 1000 | 1200 | ISO 8791-2 |
| Stretch CD, % | | 6.0 | 6.0 | 6.0 | 6.0 | 6.0 | 6.0 | ISO 1924-3 |

OBA free





Trayforma[™] PP

Bleached tray board for microwave oven

Certificates

Quality management ISO 9001 Environmental management ISO 14001 Product safety FSSC 22000 Product safety ISO 22000 Occupational health and safety ISO 45001 Energy management ISO 50001





FSC and PEFC certified board available upon request.



Paperboard is recyclable

Key characteristics and main enduses

Trayforma is an eco-friendly high-quality board specially designed for pressed and folded trays, which have high requirements for formability. Trayforma is food-safe, ecological as a renewable material, and works exceptionally well in tray pressing.

With heat-resistant PP coating, trays made of Trayforma PP can be used for heating or warming up prepared and semi-prepared foods. The PP coating also provides protection against humidity and grease. Trayforma delivers excellent results in flexographic and offset printing to showcase brands. It's easy convertability and stability offers many opportunities for shelf differentiation.

Printing and finishing techniques

The product can be used for flexo and offset printing. It is important to ensure that also the ink and varnish to be used are suitable for high temperatures in the oven use. It is important to check possible limitations of the printing and converting equipment and ensure that the basis weight of the board fits the tooling to be used.

Storage recommendations

For optimal printing results, the moisture proof wrapping should not be removed until the board has reached the temperature of the press room.

| Pallet/Reel Weight (kg) | Difference in temperature between board and press room (press room temp. approx. 20°C) | | | | | |
|-------------------------|--|--------|--------|--|--|--|
| | 10°C | 20°C | 30°C | | | |
| 400 kg | 2 days | 2 days | 3 days | | | |
| 800 kg | 2 days | 3 days | 4 days | | | |
| 1200 kg | 2 days | 4 days | 5 days | | | |

The product properties, according to the specifications, are guaranteed for 12 months after the production date. In order to ensure product safety, the product must be well wrapped and stored indoors, sheltered from rain and snow. The recommended storage conditions are 50-55% relative humidity and 20-23°C.

